

LIST OF FIGURES

2. LITERATURE REVIEW

Figure 1 The Fringed-Micelle Model for Semicrystalline Polymers (Adopted from Ref. 3).	9
Figure 2 Regularly folded lamellar structure (top) in comparison to a more random "switchboard" model (bottom) (Adopted from Ref. 10).....	10
Figure 3 A polymer spherulite with chain folded lamellae. The branch points are also indicated (Adopted from Ref. 7).	13
Figure 4 Schematic representation of (a) linear polyethylene and (b) ethylene/1-butene copolymer (Adopted from Ref. 2).....	16
Figure 5 The exclusion (top) and uniform inclusion (bottom) models as the extreme cases for crystalline random copolymers (Adopted from Ref. 40)	24
Figure 6 Equilibrium distribution of crystalline sequences in a random ethylene/1-butene copolymer (Adopted from Ref. 36).	36
Figure 7 Structure of cyclopentadienyl amide titanium catalyst used in the synthesis of ethylene/ α -olefin copolymers (Adopted from Ref. 66).....	41
Figure 8 Classification of copolymer morphology (Adopted from Ref. 85).....	49
Figure 9 Orthorhombic crystal structure for polyethylene (Adopted from Ref.2)	68
Figure 10 The two allowed phase relationships of chain vibrations in the unit cell of polyethylene. The short arrows represent the direction of motion of the corresponding atoms. The long and broad arrows represent the direction of the instantaneous dipole moment (Adopted from Ref. 122).....	69

3. EXPERIMENTAL

Figure 1 The displacements corresponding to the baseline, sapphire and the copolymer, EB-912 during cooling from the melt (180°C) at 20°C/min.....	84
---	----

Figure 2 Absolute heat capacities, the C_p baseline and the "final" heat capacities for EB-912 cooled from the melt at 20°C/min.....	86
Figure 3 Evolution of the low endotherm for EB-883 quenched from the melt (160°C) to -20°C and subsequently crystallized at $T_x = 40^\circ\text{C}$ for various times. The Gaussian peaks used in the deconvolution are also shown (black lines). The red curve represents the low endotherm. (a) Quenched, (b) $t_x = 1$ min, (c) $t_x = 60$ min.	88

4. MATERIALS CHARACTERIZATION

Figure 1 Numbering scheme for the identification of carbon atoms in the ^{13}C NMR spectra of an ethylene/ α -olefin copolymer (Adopted from Ref. 1).....	100
Figure 2 Ethyl branches in the 1,3-position (Adopted from Ref. 1).	100
Figure 3 Ethyl branches in the 1,2-position, indicating head-to-head addition.....	100
Figure 4 Comparison of the densities of ethylene/1-butene copolymers from the present study (\bullet) with the model hydrogenated polybutadienes from Krigas <i>et al.</i> (o). The value of comonomer content used is from Table 2.	114
Figure 5 Effect of residence time at 23°C on the bulk density of EB-874 (from L. Richardson)	116

5. DIFFERENTIAL SCANNING CALORIMETRY

Figure 1 Degrees of crystallinity at -20°C for ethylene/1-butene, ethylene/1-pentene and ethylene/1-hexene copolymers (after cooling from the melt at 5°C/min) as a function of comonomer content. The crystallinity data for HPBs ^{6,7} , are also included.....	122
Figure 2 Peak melting temperatures for ethylene/1-butene, ethylene/1-pentene and ethylene/1-hexene copolymers as a function of comonomer content. The peak melting temperatures for HPBs ⁷ are also included.	123

Figure 3 Corrected heat capacities for EB-912 during cooling from the melt at different rates	124
Figure 4 Degrees of crystallinity as a function of temperature obtained at different cooling rates from the melt for linear polyethylene (from Dr. A. Alizadeh)..	127
Figure 5 Degrees of crystallinity as a function of temperature obtained at different cooling rates from the melt for ethylene/1-butene copolymers of various branch contents	128
Figure 6 Degrees of crystallinity as a function of temperature obtained at different cooling rates from the melt for ethylene/1-pentene copolymers of various branch contents.....	129
Figure 7 Degrees of crystallinity as a function of temperature obtained at different cooling rates from the melt for ethylene/1-hexene copolymers of various branch contents	130
Figure 8 Degrees of crystallinity as a function of temperature for EB-894 during cooling at 20°C/min from the melt and during subsequent heating at 20°C/min.....	132
Figure 9 DSC thermograms for EB-883 after crystallization for various times at 20°C.....	135
Figure 10 Curves obtained by subtraction of heating traces after finite crystallization times at 20°C from that of the quenched sample for EB-883	136
Figure 11 Relative positions of the low endotherms for EB-912 after crystallization for various times at 20°C.....	139
Figure 12 Relative positions of the low endotherms for ethylene/1-butene copolymers after crystallization for various times at 20°C.....	140
Figure 13 Relative positions of the low endotherms for ethylene/1-pentene copolymers after crystallization for various times at 20°C.....	141
Figure 14 Relative positions of the low endotherms for ethylene/1-hexene copolymers after crystallization for various times at 20°C.....	142
Figure 15 Relative positions of the low endotherms for ethylene/1-butene, ethylene/1-pentene and ethylene/1-hexene copolymers after crystallization for various times at 20°C.....	143

Figure 16 Typical Avrami plot for EB-912 after crystallization for various times at 20°C. The parameters corresponding to short (top) and long (bottom) times are also indicated.....	152
Figure 17 Crystallization rate constant, k as a function of branch concentration for ethylene/1-butene copolymers	154
Figure 18 DSC thermograms for EB-912 after crystallization for long times at different crystallization temperatures	157
Figure 19 DSC thermograms for EB-912 after crystallization for various times at 100°C	158
Figure 20 Peak positions of the endotherms for EB-912 after crystallization at various times for T_x ranging from 20 to 100°C.....	159
Figure 21 Avrami plots for EB-912 (with ~ 5 mole % butene) crystallized at various temperatures. The numbers indicate $T_x/(n)$	161
Figure 22 Normalized rate constant, k , for EB-912 as a function of crystallization temperature	164
Figure 23 Variation of B as a function of crystallization temperature for the ethylene/1-butene copolymers of various branch contents.....	165
Figure 24 Avrami exponents, n as a function of crystallization temperature for the ethylene/1-butene copolymers of various branch contents.....	166
Figure 25 Variation of the cross-over temperature, T^* , with comonomer content for the ethylene/1-butene copolymers	169

6. ATOMIC FORCE MICROSCOPY

Figure 1 Atomic Force Micrograph of EB-928 (~2 mole % 1-butene); Quenched sample (Cooling rate > 40°C/min).....	184
Figure 2 Atomic Force Micrograph of EB-912 (~5 mole % 1-butene); Quenched sample (Cooling rate > 40°C/min)	185
Figure 3 Atomic Force Micrograph of EB-894 (~9 mole % 1-butene); Quenched sample (Cooling rate > 40°C/min)	186

Figure 4 Atomic Force Micrograph of EB-883 (~13 mole % 1-butene); Quenched sample (Cooling rate > 40°C/min)	187
Figure 5 Atomic Force Micrograph of EB-879 (~14 mole % 1-butene); Quenched sample (Cooling rate > 40°C/min)	188
Figure 6 Atomic Force Micrograph of EB-874 (~16 mole % 1-butene); Quenched sample (Cooling rate > 40°C/min)	189
Figure 7 Atomic Force Micrograph of EP-910 (~ 5 mole % 1-pentene); Quenched sample (Cooling rate > 40°C/min)	190
Figure 8 Atomic Force Micrograph of EH-910 (~ 4 mole % 1-hexene); Quenched sample (Cooling rate > 40°C/min)	191
Figure 9 Atomic Force Micrograph of EB-912 (~5 mole % 1-butene) at a higher magnification; Quenched sample (Cooling rate > 40°C/min).....	192
Figure 10 Atomic Force Micrograph of EB-912 (~5 mole % 1-butene) (a) quenched sample (cooling rate > 40°C/min.) (b) slowly cooled sample (cooling rate = 1°C/min.).....	197

7. FOURIER TRANSFORM INFRARED SPECTROSCOPY

Figure 1 Influence of temperature on the infrared spectrum of EB-883 (~ 13 mole % 1- butene) (Arrow indicates increasing temperature)	202
Figure 2 Peak position and integrated intensity of the 775cm ⁻¹ band as a function of comonomer content for the ethylene/1-butene copolymers	205
Figure 3 Comparison of fitted melt with the experimentally obtained melt spectrum at 135°C for EB-883 with ~ 13 mole % 1-butene (● Experimental; — Fitted) ..	208
Figure 4 (a) The amorphous band estimated from mathematical modeling in comparison to the experimental semicrystalline spectrum (● Experimental spectrum; — Amorphous band from modeling), (b) the crystalline band after amorphous band subtraction with the fitted Voigt peaks (● Experimental Crystalline Band; — Fitted Voigt peaks) for EB-912 (~ 5 mole % 1-butene) at 30°C.....	209

Figure 5 Crystallinity as a function of temperature for the ethylene/1-butene copolymers (o First heating; • Cooling; Δ Second heating cycles)	212
Figure 6 (a) Infrared crystallinities of the ethylene/1-butene copolymers as a function of comonomer content, (b) infrared spectra at 25°C for the ethylene/1-butene copolymers with varying branch contents	216
Figure 7 Infrared spectra of octacosane at various temperatures (as indicated) (From Dr. A. Alizadeh).....	220
Figure 8 Ratios of I_{730}/I_{720} for linear polyethylene and an <i>n</i> -paraffin, octacosane at various temperatures (from Dr. A. Alizadeh)	221
Figure 9 Ratio of I_{730}/I_{720} for EB-912 (with ~ 5 mole % 1-butene) during (o) Heating of a quenched sample () Slow Cooling (Δ) Heating of a slowly cooled sample (A rate of 1.5°C/min was used for all three processes)	222
Figure 10 Ratio of I_{730}/I_{720} for EB-894 (with ~ 9 mole % 1-butene) during (o) Heating of a quenched sample () Slow Cooling (Δ) Heating of a slowly cooled sample (A rate of 1.5°C/min was used for all three processes).....	223
Figure 11 Ratio of I_{730}/I_{720} for EB-883 (with ~ 13 mole % 1-butene) during (o) Heating of a quenched sample () Slow Cooling (Δ) Heating of a slowly cooled sample (A rate of 1.5°C/min was used for all three processes)	224
Figure 12 Deconvolution of the crystalline portion of the infrared spectrum. The sample indicated is EB-883 (~ 9 mole % 1-butene) at 25°C	229
Figure 13 Variation of the integrated intensity of the second crystal structure as a function of temperature for the copolymers, (o) EB-912 (~ 5 mole % 1-butene), (Δ) EB-894 (~ 9 mole % 1-butene) and ()EB-883 (~ 13 mole % 1-butene)	231
Figure 14 Variation in the ratio, I_{730}/I_{720} with comonomer content for the ethylene/1- butene copolymers.....	238